

ABSTRACT OF THE DISCLOSURE

A heat-resistant, austenitic spheroidal graphite cast iron has a composition comprising 1-4.5% by weight of Mo, and 0.001-0.5% by weight of Sn and/or Sb as (2Sn + Sb). It preferably has a composition comprising
5 1-3.5% of C, 1-6.5% of Si, 3% or less of Cr, 10-40% of Ni, 1-4.5% of Mo, 0.001-0.5% of Sn and/or Sb as (2Sn + Sb), and 0.1% or less of a graphite-spheroidizing element, on a weight basis.